

DESCRIPTION

Two Part Rubber Sealant Compound

TEMPERATURE RANGE

-60°F to 500°F

APPLICATIONS

Gasket coating, threads, or void fill. Mild steam, water applications, Acetic Acid, Mineral Oil, Natural Gas, Propane, various chemicals.

CHARACTERISTICS

Cures to a solid with good adhesion. Remains flexible from -60°F to 500°F with intermittent exposure to 600°F.

CURE TIME

6.5 hours.

BASE/CATALYST RATIO

10:1

WORKING TIME

45 minutes

NOTE

For additional bridging can be mixed with Deacon Dry-Pak mixtures.

SHELF LIFE

Two years in closed containers.
Store below 90°F.

PACKAGED

One Pint Kits, One Quart Kits, and One Gallon Kits.

DIRECTIONS

Please be advised that we recommend a top and bottom ring of braided packing still be installed for containment, especially when tolerances are in question.

FOR INDUSTRIAL USE BY PROFESSIONALLY TRAINED PERSONNEL ONLY.

CONSULT SDS & TECH SHEET FOR ALL SAFETY, TECHNICAL, & WARRANTY INFORMATION BEFORE USE. **NOT RECOMMENDED FOR USE ON NUCLEAR APPLICATIONS**

LIMITED WARRANTY

For warranty information please visit http://www.jetlube.com/pdf/Limited_Warranty_At_Delivery_Deacon.pdf You can also email us at sales@deaconindustries.com or write to the Sales Department at the address below.