

DESCRIPTION

NCS-30[®] nonconductive thread compound is a premium quality, nonmetallic compound containing carbon-based fibers and additives and other natural extreme pressure and anti-wear additives. These are blended into **JET-LUBE's** high temp calcium complex base grease. This new base grease offers the additional advantage of superior adhesion to wet steel surfaces, resistance to water wash-off, and most drilling muds. **Especially effective for invert or high-pH muds.**

- Excellent performance on high-chrome or nickel alloys
- Contains no metals
- NSF H2 Registered
- Extreme-pressure additives provide additional protection against seizing and galling
- Nonconductive for MWD applications
- Provides maximum protection on Wedge Thread^{™*} drill string connection designs
- High frictional properties ideal for casing drilling applications

NCS-30 is formulated to prevent excessive circumferential makeup by increasing the coefficient of friction under compressive forces. As stress levels rise above 50% of yield, the friction factor increases, limiting downhole makeup. Full hydraulic joint efficiency is maintained allowing joint shoulder faces to mate completely without standoff or deformation. **NCS-30**, with frictional properties similar to **KOPR-KOTE[®]**, has been designed to utilize the makeup charts in API RP7G multiplied by its 1.15 friction factor on API connections. Premium drill string connections such as HI-TORQUE[®] (HT), eXtreme[®] Torque (XT[®]), and XT-M[™] connections, etc., utilize make-up torques based upon thread compound friction factors of 1.0. Therefore, use the torque provided by the premium connection manufacturer. Adjusting make-up torque based on thread compound friction factor may still be advised. Friction factors for **NCS-30** were developed using full scale API tool joint connections.

- For a “Yellow”-rated product, use NCS-30[®] ECF[™].
- Designed for optimum performance on all Rotary-Shouldered connections such as Tool Joints and Drill Collars. It can also be used on premium/proprietary thread designs such as Double-Shouldered, Wedge Thread^{™*}, and other types of mechanical seal designs. It may also be used on certain non-interference tubing thread designs when properly torque compensated.

* Trademark of Hydril Company.

PRODUCT CHARACTERISTICS

Thickener	Calcium Complex
Fluid Type	Petroleum
Dropping Point (ASTM D-2265)	≥450°F (232°C)
Specific Gravity, typical	1.30
Density (lb/gal), typical	10.95
Oil Separation (ASTM D-6184)	<3.0
WT. % LOSS @ 212°F (100°C)	
Flash Point (ASTM D-92)	> 430°F (221°C)
NLGI Grade	1
Penetration @ 77°F	300 – 330
(ASTM D-217)	
Copper Strip Corrosion	1A, typical
(ASTM D-4048)	
Friction Factor *	
Relative to API RP 7G	1.15 (drill strings)
Proprietary Connections	Consult Manufacturer
Service Temperature	
Oilfield/Mining/Construction Drilling	-20°F (-29°C) to 500°F (260°C)
Industrial Anti-seize Applications	-65°F (-54°C) to 2600°F (1427°C)

* Many factors such as pipe size, thread geometry, drilling mud contamination, etc. affect the friction factor. This is a relative number and, in all applications experience, and prior knowledge should be used to adjust make-up torque accordingly.

Environmental Rating:

UK CEFAS Group E

For package types and part numbers

www.jetlube.com/resources/product-index/

Limited Warranty

www.jetlube.com/assets/documents/Jet-Lube_Warranty.pdf