

# SS-30<sup>™</sup> EXTREME

# SHEEN FREE, SUBSEA, ANTI-CORROSION. ANTI-SEIZE

## **DESCRIPTION**

SS-30™ Extreme literally copper plates mating and sliding surfaces to provide protection against seizure, galling, and heat-freeze. Its high content of copper particles prevents metal-to-metal contact, maintaining lubrication qualities under wide variations of temperature, expansion, contraction, and cyclic pressures and loadings.

**SS-30 Extreme** has a high content of micro size, pure copper flakes that are homogenized into a calcium sulfonate complex grease with exceptional corrosion resistance and anti-wear properties. It contains no lead, zinc, molydisulfide, or graphite, does not require mixing, and will not separate, settle out, harden, or dry out in storage. It is fortified with anti-oxidants and corrosion inhibitors. This formula is sheen free.

**SS-30 Extreme** is easy to use, brushes on readily, and adheres tenaciously - even on wet or oily surfaces. It brushes evenly into thread roots and over any surface, assuring complete and efficient coverage.

**SS-30 Extreme** is specially formulated for subsea fittings, protecting them from galling and corrosion. It works equally well on a wide range of similar and dissimilar metals and mating parts, including steel, cast iron, brass, copper, plastics, titanium gasket materials and packings. Excellent for stainless steel.

- · Lead, Graphite & MoS2 Free
- Protects against seizure, heat-freeze, galling, rust and corrosion
- Sheen Free
- · Brushes on easily
- Highly adhesive on both wet and dry surfaces
- "Copper Plates" to prevent metal-to-metal contact
- · Will not run, drip, or settle out
- Color Copper
- · High electrical conductivity

#### **APPLICATIONS**

**SUBSEA:** For subsea nuts and bolts where long-term corrosion resistance and anti-galling are primary concerns.

# **GENERAL USES:**

Studs Screws Bushings Nuts Slides Flanges

Bolts Press Fits Sliding Surfaces

NOTE: Not for use on oxygen lines.

**CONFORMS TO:** 

Military Specification MIL-PRF-907F **SERVICE RATING:** 

-65°F (-54°C) to 1800°F (982°C)

## PRODUCT CHARACTERISTICS

Thickener Calcium Complex
Fluid Type Group I Oil
Color/Appearance Copper Paste

Dropping Point (ASTM D-566)

Specific Gravity

Density (lb/gal)

Oil Separation

WT. % LOSS @ 212°F (100°C)

Flash Point (ASTM D-92) >500°F (260°C)

NLGI Grade 1½
Nut-Factor/Nut Factor\* 0.13
(I" B-7 Studs @ 60k – 80k psi Contact Stress)

 $*(T = K \times D \times F)$  where:

 $\dot{T}$  = torque,  $\dot{K}$  = nut factor, cometimes incorrectly called the friction factor, D = bolt diameter, and F = bolt tension generated during tightening.

Penetration @77°F (ASTM D-217) 280 - 300

Copper Strip Corrosion 1A (ASTM D-4048)

Shell 4-Ball (ASTM D-2596)

Weld Point, kgf 250

Load Wear Index Not Applicable

Salt Fog Resistance 100

20% NaCl @ 100°F, Hrs. Free of Corrosion (ASTM B-117)

For package types and part numbers contact <a href="mailto:sales@jetlube.com">sales@jetlube.com</a>.

#### LIMITED WARRANTY

For warranty information please visit

http://www.ietlube.com/pdf/Jet-Lube Warrantv.pdf