

MATRIX® EP EXTREME-SERVICE GREASE

Whitmore® Matrix® is a calcium sulfonate complex grease that is highly recommended for difficult applications such as extreme pressure, water, heat, or chemical attack.

The thickener system in Whitmore Matrix has a protective effect similar to that of molybdenum disulfide, protecting equipment from wear under difficult conditions of extreme load and slow speed.

Whitmore Matrix helps neutralize acids and also resists reacting with caustic materials. Whitmore Matrix grease has prevented corrosion despite years of exposure to phosphoric acid fumes.

A continuous temperature of 400°F (200°C) is within its safe range. It can withstand 550°F (288°C) continuously, provided the bearing is replenished every 30 minutes with normal quantities of grease. Occasional temperature spikes to 600°F (315°C) can be sustained for 5 to 10-minute periods without melting or carbonizing.

Whitmore Matrix EP 2 may be used at DN speeds up to 250,000 and is the preferred grade for electric motor bearings.

Whitmore Matrix EP 2 meets the Bucyrus International specification for multi-purpose grease (SD 4711). It also meets the following standards per DIN 51502: KP2R -20.

Andritz Separation, Inc. of Arlington, Texas has issued an approval of Whitmore Matrix EP Grease for use in the automatic lubrication systems of their tilting pan filters.

BENEFITS:

- **LONG LIFE** - reduced relubrication frequency.
- **WATER RESISTANT** - seals out water, even in underwater applications.
- **WIDE SPEED RANGE** - recommended for use in electric motor bearings as well as slow moving bearings and bushings.

APPLICATIONS:

Water / Chemicals: Phosphate processing, suction and wet end rolls on paper machines, outdoor cranes and ship lifts, boat trailer wheel bearings and other marine applications.

Highly Loaded Equipment: Pellet mills, shaker screens, belt conveyor pulleys, slewing bearings, pin and bushing, centrifuges, hammermills, sealed work roll bearings, fan bearings and many others.

High Temperature Applications: Oven conveyor bearings, plastic extruder bearings, rotary unions on roto-molders.

Automotive and Earthmoving Applications: Wheel bearings, U-joints, ball joints, pin-and-bushing pivot points and slewing bearings.

ASTM #		TYPICAL CHARACTERISTICS			
	Grade	Winter	EP 0	EP 1	EP 2
D-217	Penetration Range	390-410	355-385	310-340	265-295
D-2265	Dropping Point, °F (°C)	350 (177)	460 (238)	500 (260)	500 (260)
D-445	Kinematic Viscosity (Base Oil) cSt @ 40°C cSt @ 100°C	44 6	125 12	125 12	125 12
D-445	Kinematic Viscosity (with Polymer) cSt @ 40°C cSt @ 100°C	82 9.6	800 47	800 47	800 47
D-2596	Four Ball EP Weld Point, kg	500	500	800	800
D-2266	Four Ball Wear, Scar Width, mm	0.60	0.60	0.60	0.45
D-4049	Water Spray-Off, % Loss	--	--	--	<1
D-1264	Water Washout, % Loss	--	--	<2	<2
D-1743	Rust Test	Pass	Pass	Pass	Pass
	Thickener Type	Calcium Sulfonate	Calcium Sulfonate	Calcium Sulfonate	Calcium Sulfonate
OEM Standard	Low Temperature Pumpability Lincoln Ventmeter @ 400 psi, °F (°C)	--	-20 (-29)	12 (-11)	34 (1)

PACKAGING

Plastic Totes (Non-returnable)	Drums	Kegs	Pails	Cartridges 50 Per Case
-----------------------------------	-------	------	-------	---------------------------

For warranty information, scan the QR code.

whitmores.com

An ISO 9001 and ISO 14001 registered company

